Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A method for determining the degree of loading of a waterproofing agent within a planar carbon substrate for use in an electrochemical fuel cell, comprising the steps of:

measuring the transmittance of light through the carbon substrate when in an unloaded state;

measuring the transmittance of light through the carbon substrate when in a loaded state; and

comparing the difference in transmittance from the unloaded state to the loaded state and therefrom determining the degree of loading of the waterproofing agent within the carbon substrate.

- 2. (Original) The method of claim 1 wherein the carbon substrate is a carbon fiber paper.
- 3. (Original) The method of claim 1 wherein the carbon substrate is a carbon cloth.
- 4. (Original) The method of claim 1 wherein the carbon substrate is a continuous web impregnated with an electrically conductive filler.
- 5. (Original) The method of claim 1 wherein the waterproofing agent is polytetrafluorethylene.

Application No. 10/644,072 Reply to Office Action mailed May 18, 2005

- 6. (Original) The method of claim 1 wherein the waterproofing agent is selected from the group consisting of polyethylene, polypropylene and ethylene-propylene copolymer.
- 7. (Original) The method of claim 1 wherein the degree of loading of the waterproofing agent within the carbon substrate when in the loaded state ranges from 1% to 50% by weight.
- 8. (Original) The method of claim 1 wherein the degree of loading of the waterproofing agent within the carbon substrate when in the loaded state ranges from 4% to 30% by weight.
- 9. (Original) The method of claim 1 wherein transmittance is measured at 4000 to 7000 Å.
- 10. (Original) The method of claim 1 wherein light is provided by a light source selected from the group consisting of halogen, tungsten, fluorescent and UV lamps.
- 11. (Original) The method of claim 1 wherein the carbon substrate has a thickness of less than 0.5 mm.